

Scrim banner blackout 710

matt 8215 - 710 g/m²

Heavy, 710 g/m², white, reinforced, polyester fabric, matt PVC coated banner with a black block out coating.

Advantages

- Indoor/outdoor banners
- Advertising, exhibitions
- Excellent print quality
- Two side printable, opaque

Storage conditions

Shelf life: 2 years, temperature 21°C, relative humidity 50%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

Print Conditions

Best results are obtained between 18-25°C and 35-70% RH.

Environment, Health & Safety

No material safety datasheet required. Waste not suitable for recycling

Outdoor use

This material is developed for outdoor and indoor use.

Lamination

Compatibility

Hot	Warm	Cold
1	1	1
3=excellent	2= fair	1= not recommended

Hot: heat activated: 105°C - 130°C
Warm: heat activated: 85°C - 95°C
Cold: pressure sensitive

Colour Profiles

Sihl Direct b.v. develops high quality colour profiles for media / ink / printer / Rip combinations. Check availability of profiles for your printer at the download section www.sihl.nl or contact us at +31(0)73-6441044.

ING Bank 's-Bosch 67.47.92.742
BTW NL805593445B01
IBAN NL97 INGB 0674 7927 42
BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponereerd d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
Mangaan 8
5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
telefax +31(0)73 6441212
e-mail sihl@sihl.nl
internet www.sihl.nl
K.v.K. 's-Bosch 160.55.676

Scrim banner blackout 710matt 8215 - 710 g/m²

List of Printers

Printer	Ink	Quality
Océ CS6060/6100	Solvent	Excellent Use of external dryer is advised
Océ CS9065/9090 (low solvent)	Solvent	Excellent
Océ CS9065/9090 (eco solvent)	Solvent	Excellent
Océ CS7070/7075/7100	Solvent	Excellent
Océ Arizona series	Solvent	Excellent
Seiko color painter 64S / 100S	Solvent	Excellent Use of external dryer is advised
HP Designjet 8000s/9000s/10000s	Solvent	Excellent Use of external dryer is advised
Mutoh rockhopper (eco solvent ultra)	Solvent	Excellent
Mutoh spitfire (mild solvent)	Solvent	Excellent
Mutoh Toucan/Osprey/Phoenix	Solvent	Excellent
Agfa grand sherpa	Solvent	Excellent
ColorSpan display maker 72/98 UVX/UVR	Solvent	Excellent
ColorSpan display maker 72s/98s	Solvent	Excellent
Gandiinnovations Jeti 33xx/5000	Solvent	Excellent
Mimaki JV3 series	Solvent	Excellent
Roland Soljet/Versacam series	Solvent	Excellent
NUR, Scitex, Vutek	Solvent	Excellent

ING Bank 's-Bosch 67.47.92.742
 BTW NL805593445B01
 IBAN NL97 INGB 0674 7927 42
 BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponoerd d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
 Mangaan 8
 5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
 telefax +31(0)73 6441212
 e-mail sihl@sihl.nl
 internet www.sihl.nl
 K.v.K. 's-Bosch 160.55.676

Scrim banner blackout 710**matt 8215 - 710 g/m²****Physical Properties**

Weight	710 ± 60 g/m ²	EN ISO 2286-2	Breaking load*	250/140 daN/5cm	EN ISO 1421
Thickness	560 µm	ISO 534	Breaking extension*	18/18%	EN ISO 1421
Fabric Mass	130 ± 10 g/m ²	EN ISO 2286-2	Tear Strength*	14.0/10.0 daN	DIN53363
Whiteness (L,a,b)	92.6, -1.03, 3.75		Colour fastness	Min. 6	EN ISO 105-B02
Opacity	100%		Coating fastness	> 7.5 daN/50mm	EN ISO 2411
Flammability (mm/min)	<100	DIN 75200			

*MD/CD

Available widths (mm)

3"Core

1372

1600

1900

2200

2500

The data provided in this product data sheet are values for orientation only.

Before using our print media please check their suitability for your printer and for your intended application. We do not take any liability for failures or damages resulting from technically modified printing inks and/or printers as technical specifications are subject to change.

ING Bank 's-Bosch 67.47.92.742
 BTW NL805593445B01
 IBAN NL97 INGB 0674 7927 42
 BIC/SWIFTCODE INGBNL2A

Op al onze aanbiedingen en overeenkomsten zijn de ICT-Office Voorwaarden van toepassing, gedeponereerd d.d. 14 januari 2009 bij de Kamer van Koophandel te Midden-Nederland onder nummer 30174840. De afnemer heeft van deze voorwaarden kennis genomen en verklaart zich akkoord met de inhoud van deze voorwaarden. Op verzoek worden de ICT-Office Voorwaarden kosteloos nogmaals toegezonden.

Sihl Direct bv
 Mangaan 8
 5234 GD 's-HERTOGENBOSCH

telefoon +31(0)73 6441044
 telefax +31(0)73 6441212
 e-mail sihl@sihl.nl
 internet www.sihl.nl
 K.v.K. 's-Bosch 160.55.676